

RESEARCH ARTICLE

Preparation and biocompatibility of 3D-printed partially degradable Ta-Mg interpenetrating composites

Supplementary file




Figure S1. Thickness of the reaction layer in the Ta–Mg composite. Scale bar: 50 μm.

Table S1. Thickness of the reaction layer

Measurement	Thickness (μm)
1	9.906228
2	10.1574
3	8.285511
4	9.856029
5	9.572122